## Technical data sheet



## **Aquawood Finapro 15**

5187

Water-based, matte, thick-film glaze for wooden windows and front doors for industrial and professional use

System-matched in 3-layer-structure

#### **PRODUCT DESCRIPTION**

#### General

Matt, water-based, breathable thick-film glaze with very good weather resistance and good transparency. The product is characterised by high block resistance, very good impact resistance, fast water resistance, short drying times, natural matt appearance and good tactile properties.


## Special properties and standards





Safety of toys; migration of certain elements (free of heavy metals)





Perspiration and saliva-proof properties



Proof of suitability according to DIN EN 927-2



#### French ordinance DEVL1104875A

Marking of construction coating products for their emission of volatile pollutants: A+

#### Application area







For dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows and front doors.

For humid areas (e.g. indoor pools) only with a special coating system.

For non-dimensionally stable timber components we recommend thin-film systems such as Lignovit Lasur (5315) or Pullex Plus-Lasur (4415).

Please refer to the corresponding technical data sheets of the products.

#### **PROCESSING**

#### **Processing instructions**





- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- The optimal conditions for use are between 15 25 °C with a relative atmospheric humidity between 40 - 80 %.

1-1 IMC 5187 | 01/25 | replaces 1-0

- Too high dry film thicknesses from approx. 120 µm reduce the diffusion capacity and should thus be avoided.
- Sealants must be compatible with the coat and may only be applied once the paint has dried through. Sealing profiles with plasticizers tend to stick together in combination with paints. Please only use those types that have been tested.
- We do not recommend applying two layers of Aquawood Finapro 15 (5187) with intermediate sanding, because due to the content of a matting wax, a polishing effect and therefore a poor intermediate adhesion is possible.
- An intermediate coating with Aquawood Intermedio ISO (5705) is recommended to prevent air inclusions in deep-pored hardwood species and to avoid film interference on larch.
- When changing from Aquawood Finapro 15 (5187) to other water-based paint systems, care must be taken to adequately clean the pipes and spray equipment, preferably with warm water.
- Any change in the processing sequence, environmental conditions, nonobservance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.
- Please follow our ARL 300 Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - General part along with all standards and guidelines for window construction.

#### **Application technique**







	Airless	Airless air-supported (Airmix <sup>®</sup> , Aircoat, etc.)	Cup gun
Spraying nozzle Ø (mm)		0,28 - 0,33	1,8 – 2,0
Spray nozzle (Ø inch)		0,011 – 0,013	-
Nozzle angle (°)		20 – 40	-
Spraying pressure (bar)		80 – 100	3-4
Vaporizer Air (bar)	-	0,5 – 1,5	-
Spraying distance (cm)		25	
Diluent		Water	
Diluent amount added (%)		0 – 5	10
Applied quantity per application (g/m²)		225 – 300	
Wet film (μm)		225 – 300	
Dry film complete coating system (µm)		80 – 120	

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

#### **Drying times**

(at 23 °C and 50 % rel. humidity)



Dust-dry (ISO 1517)	ca. 1 hour(s)
Tack-free	ca. 2 hour(s)
Stackable with PE fine foam spacers at room temperature	ca. 5 hour(s)
Stackable with PE fine foam spacers after forced drying 20 minutes evaporation zone / dripping zone 90 minutes drying stage (35 – 40 °C) 20 minutes cooling stage	ca. 130 minutes
Recoatable	ca. 12 hour(s)

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

# Cleaning the working equipment





With water immediately after use.

To remove dried paint residues we recommend using Aqua-Cleaner (8029) (diluted 1:1 with water).

	SUBSTRATE
Type of substrate	Wood in accordance with the guidelines for window construction.
Substrate property	The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.
Wood moisture	13 % ± 2 %
	COATING SYSTEM
General	The following coating systems are exemplary.
Impregnation	1 x Aquawood Primo (5453)
. 5	Intermediate drying: approx. 4 hour(s)
	Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.
	Please follow our ARL 056 - Working guideline for the use of wood preservatives.
Intermediate coat	Softwoods:
	1 x Aquawood Intermedio DQ (5706)
	Hardwoods and Larch:
	1 x Aquawood Intermedio ISO (5705)
	Intermediate drying: approx. 2 hour(s)
	Please refer to the corresponding technical data sheets of the products.
	. 3

Intermediate sanding	Grit size 220 – 240 Remove sanding dust.
Finishing coat	1 x Aquawood Finapro 15 (5187)
For front doors	An additional application of Aquawood Protect (5128) (colourless two-component varnish) is necessary.  Please refer to the corresponding technical data sheet of the product.
	MAINTENANCE
Care	The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary.
	Annual cleaning with Top-Cleaner (7208) and maintenance with Top-Care (7227) in the package with Windoor Care-Set (7229).
	Please refer to the corresponding technical data sheets of the products.
	Please follow our <b>ARL 304 - Working guideline for coating dimensionally</b> stable and limited dimensionally stable construction elements -
	Maintenance and repair.
	Maintenance and repair.  ORDERING INFORMATION
Size of trading unit	·
Size of trading unit  Colour shades / Glosslevels	ORDERING INFORMATION
	ORDERING INFORMATION  20 kg, 120 kg polybarrel  Colour shades can be obtained using the ADLER colour mixing system
Colour shades / Glosslevels	ORDERING INFORMATION  20 kg, 120 kg polybarrel  Colour shades can be obtained using the ADLER colour mixing system ADLERMix.  Base paint(s):
Colour shades / Glosslevels	ORDERING INFORMATION  20 kg, 120 kg polybarrel  Colour shades can be obtained using the ADLER colour mixing system ADLERMix.  Base paint(s): Aquawood Finapro 15 Basis W30 (5187000030)  The final colour is basically obtained from the inherent colour of the wood, the applied quantity, the colour of the impregnation and the colour of the
Colour shades / Glosslevels	ORDERING INFORMATION  20 kg, 120 kg polybarrel  Colour shades can be obtained using the ADLER colour mixing system ADLERMix.  Base paint(s): Aquawood Finapro 15 Basis W30 (5187000030)  The final colour is basically obtained from the inherent colour of the wood, the applied quantity, the colour of the impregnation and the colour of the finishing coat.  In order to ensure uniformity of the colour shade, use only material with the
Colour shades / Glosslevels	ORDERING INFORMATION  20 kg, 120 kg polybarrel  Colour shades can be obtained using the ADLER colour mixing system ADLERMix.  Base paint(s): Aquawood Finapro 15 Basis W30 (5187000030)  The final colour is basically obtained from the inherent colour of the wood, the applied quantity, the colour of the impregnation and the colour of the finishing coat.  In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.  It is recommended to prepare a trial colour sample on the original substrate

#### Supplementary products

Aqua-Cleaner 8029 (8029)
Aquawood Intermedio DQ (5706)
Aquawood Intermedio ISO (5705)
Aquawood Primo (5453)
Aquawood Primo A4 (5454)
Aquawood Primo A5 (5455)
Aquawood Primo A6 (5456)
Aquawood Primo A6 (5456)
Aquawood Protect (5128)
Lignovit Lasur (5315)
Pullex Plus-Lasur (4415)
Top-Care (7227)
Top-Cleaner (7208)
Windoor Care-Set (7229)

#### **FURTHER DETAILS**

### Durability / storage





Min. 1 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above  $30\,^{\circ}$ C).

Close opened containers well and use up the content as soon as possible.

#### **Technical specifications**

VOC content of the ready-to-use mixture: EU limit for Aquawood Finapro 15 (Cat A/e): 130 q/l.

Aquawood Finapro 15 contains maximum 20 g/l VOC.

## Giscode

BSW20

# DGNB (German Sustainable Building Council)

Quality level 4 (with factory coating)

#### Safety information



The product is only suitable for the industrial and professional use.

When sanding, use at least a P2 dust filter as personal safety equipment to protect against abrasive and wood dust. In case of hardwood (especially for Beech, Oak) a dust filter P3 is recommended.

The inhalation of paint aerosols during spray application must generally be avoided. This is ensured by the proper use of a respirator (combination filter A2/P2).

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.