

Innolux Decklack GF KR

2770

Highly reactive UV roller topcoat for industrial coating of finished parquet elements (incl. cork) and furniture.

PRODUCT DESCRIPTION

General

Highly reactive UV roller topcoat with special additive to improve abrasion; very good chemical and mechanical resistance, non-yellowing.

Special properties and standards



- **ÖNORM A 1605-12 (furniture surfaces)**
Resistance to chemical reactions: 1-B1
Response to abrasion: 2-C (≥ 150 U)
Response to scratches: 4-C (≥ 1.5 N)
Flame treatment: 5-B (highly non-flammable furniture surfaces)



- **ÖNORM A 3800-1 (fire behaviour)**
In conjunction with a flame-retardant substrate:
flame-retardant, Q1, Tr 1



- **DIN 68861 (furniture surfaces)**
Part 1: Response to chemical stress: 1B
Part 2: Response to Abrasion: 2 C (> 150 to ≤ 350 U)
Part 4: Response to scratches: 4 D ($> 1,0$ to $1,5$ N)



- **DIN 53160-1 and DIN 53160-2**
Perspiration and saliva-proof properties




- **ÖNORM EN 71-3**
Safety of toys; migration of certain elements (free of heavy metals)



- **French ordinance DEVL1104875A**
Marking of construction coating products for their emission of volatile pollutants: A+

Application area




For the large-scale industrial coating of ready-made parquet elements. (incl. cork)

For the coating of furniture and interior finishing exposed to high levels of stress, such as tabletops and shelves in the kitchen and living area, bathrooms, offices and in the contract sector, fronts and permanently visible areas, surfaces used on seating furniture and not permanently visible areas. Application areas II to IV in accordance with ÖNORM A 1610-12.

PROCESSING

Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 15 °C.
- For an optimal surface quality, it is beneficial to apply the coating in 2-3 and the topcoat in 2 roller coating steps. Intermediate gelling is recommended if applying more than one coat with a roller.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please observe our **“Working guidelines for UV roller coating systems”**.

Application technique



| | Roller coater |
|--|------------------------|
| Applying device | Roller coating machine |
| Applied quantity per application (g/m ²) | ca. 3 – 6 |
| Total quantity applied (g/m ²) | max. 12 |

The product is ready to use.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

UV curing



Immediate **UV-curing** without flashing off previously:

| | Feed | |
|----------------------|----------------------|--------------|
| | Intermediate gelling | Curing |
| Hg radiator 80 W/cm | 10 - 14 m/min | 5 - 7 m/min |
| Hg Radiator 120 W/cm | 12 - 16 m/min | 7 - 10 m/min |

Avoid direct sunlight!

Cleaning the working equipment



8501

With Waschverdünner (8501) immediately after use.

SUBSTRATE

Type of substrate

Hard and softwood (solid wood-, veneer-, (coated) chipboard-, wood fibre boards)

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Substrate preparation

Calibration sanding

Hardwoods: Wood sanding Grit size 150 – 180

Softwoods: Wood sanding Grit size 120 - 150

COATING SYSTEM

| | |
|-----------------------------|---|
| Primer coat | 1 x Innolux Walzgrund Farblos (2736000200) |
| Intermediate sanding | Grit size 320 – 400 Avoid sanding straight through! |
| Topcoat | 3 – 6 g/m ² Innolux Decklack GF KR (2770) For an optimal surface quality, it is beneficial to apply the topcoat with 2 roller coating units connected in series, whereby intermediate gelling takes place after the 1st application and curing takes place after the 2nd application. Example: 1 x 4 g/m ² with reversing dosing roller Intermediate gelling with 1 Hg radiator 80 W/cm, feed rate 10 m/min 1 x 4 g/m ² with reversing dosing roller Curing with 2 Hg radiator 80 - 120 W/cm, feed rate 10 - 14 m/min |



CLEANING AND MAINTENANCE

| | |
|---------------------------------|--|
| Cleaning and Maintenance | Cleaning with Clean-Möbelreiniger (7202) an care with Clean-Möbelpflege Plus (7222). |
|---------------------------------|--|

ORDERING INFORMATION

| | |
|------------------------------------|---|
| Size of trading unit | 25 kg |
| Colour shades / Glosslevels | Innolux Decklack GF KR G15 (2770000115) |
| Supplementary products | Clean-Möbelpflege Plus (7222) Clean-Möbelreiniger (7202) Innolux Walzgrund Farblos (2736000200) Waschverdünner 8501 (8501) Please refer to the corresponding technical data sheets of the products. |

FURTHER DETAILS

| | |
|--|---|
| Durability / storage  | Min. 9 month(s) in the original sealed containers. Protect against the sun. |
| Technical specifications | Delivery viscosity: 110 – 120 seconds according to DIN 53211 (6 mm measuring cup, 20 °C) |
| Safety information  | The product is only suitable for industrial use. Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com . |